



Rhine Middle East LLC
Jafza One, Jebel Ali Free Zone POBOX 34165,
Dubai, United Arab Emirates
Tel: +971 4 81 8618

Bitumen Grade 40 / 50

Test	Test Method	Unit	Specification
Penetration @ 25°C	ASTM D5	mm/10	40/50
Softening Points (R&B)	ASTM D36	°C	52/60
Ductility @ 25°C	ASTM D113	Cm	100 min.
Flash Point °C	ASTM D92	°C	250 min.
Solubility in CS ₂ (wt) %	ASTM D4	wt%	99.5 min.
Specific Gravity @ 25°C	ASTM D70	Kg/cm ³	1.01/1.06
Loss on Heating (wt) %	ASTM D6	wt %	0.2 max.
Drop in Penetration after heating %	ASTM D5 – D6	%	20 max.

**** Above specifications are subject to change at the time of request.**