



Rhine Middle East LLC
Jafza One, Jebel Ali Free Zone POBOX 34165,
Dubai, United Arab Emirates
Tel: +971 4 81 8618

Cutback Bitumen RC-30

Test	Test Method	Unit Specification	
		Min	Max
Kinematic Viscosity at 60°C, cSt	ASTM D2170	30	60
Flashpoint, °C	ASTM D3143	-	-
Test on Residue from Distillation Test			
Penetration 25°C 100g, 5s mm	ASTM D5	80	120
Ductility 25°C 5cm/min cm	ASTM D113	100	-
Solubility in TCE %	ASTM D2042	99	-
Water %	ASTM D95	-	0.2

**** Above specifications are subject to change at the time of request.**