



Rhine Middle East LLC  
Jafza One, Jebel Ali Free Zone POBOX 34165,  
Dubai, United Arab Emirates  
Tel: +971 4 81 8618

## Emulsion Bitumen MS-2

Test	Test Method	Unit Specification	
		Min	Max
Saybolt furol Viscosity@ 50 °C (s)	ASTM D244	20	100
Storage stability, 24h (%)	ASTM D6930	-	1
Particle Charge Test	ASTM D244	Minus	
Sieve (%)	ASTM D6933	-	0.1
Residue (%)	ASTM-D244	60	-
Solubility in trichloroethylene %	ASTM D2042	97.5	-
Penetration, 25 °C, 100g, 5Sec	ASTM D5	100	200
Residue ductility, 25 °C, 5cm/min (cm)	ASTM D113	40	-

**\*\* Above specifications are subject to change at the time of request.**