



Rhine Middle East LLC  
Jafza One, Jebel Ali Free Zone POBOX 34165,  
Dubai, United Arab Emirates  
Tel: +971 4 81 8618

## Emulsion Bitumen RS-1

Test	Test Method	Unit Specification	
		Min	Max
Viscosity SSF , 25 °C (s)	ASTM D244	20	100
Viscosity SSF , 50 °C (s)	ASTM D244	-	-
Storage stability, 24h (%)	ASTM D6930	-	1
Sieve (%)	ASTM D6933	-	0.1
Residue (%)	ASTM-D244	57	-
Solubility in trichloroethylene %	ASTM D2042	97.5	-
Penetration 77°F (25°C) 100g,5s mm	ASTM D5	100	200
ductility, 77°F (25 °C), 5cm/min (cm)	ASTM D113	40	-

**\*\* Above specifications are subject to change at the time of request.**