



Rhine Middle East LLC
Jafza One, Jebel Ali Free Zone POBOX 34165,
Dubai, United Arab Emirates
Tel: +971 4 81 8618

Emulsion Bitumen SS-1

| Test | Test Method | Unit Specification | |
|---------------------------------------|-------------|--------------------|-----|
| | | Min | Max |
| Viscosity SSF , 25 °C (s) | ASTM D244 | 20 | 100 |
| Viscosity SSF , 50 °C (s) | ASTM D244 | - | - |
| Storage stability, 24h (%) | ASTM D6930 | - | 1 |
| Sieve (%) | ASTM D6933 | - | 0.1 |
| Residue (%) | ASTM-D244 | 57 | - |
| Solubility in trichloroethylene % | ASTM D2042 | 97.5 | - |
| Penetration 77°F (25°C) 100g,5s mm | ASTM D5 | 100 | 200 |
| ductility, 77°F (25 °C), 5cm/min (cm) | ASTM D113 | 40 | - |

**** Above specifications are subject to change at the time of request.**