



Rhine Middle East LLC  
Jafza One, Jebel Ali Free Zone POBOX 34165,  
Dubai, United Arab Emirates  
Tel: +971 4 81 8618

## Bitumen Grade 60 / 70

Test	Test Method	Unit	Specification
Penetration @ 25°C	ASTM D5	mm/10	60 / 70
Softening Points (R&B)	ASTM D36	°C	48/56
Ductility @ 25°C	ASTM D113	Cm	100 min.
Flash Point °C	ASTM D92	°C	232 min.
Solubility in TCE	ASTM D4	wt%	92.5 min.
Specific Gravity @ 25°C	ASTM D70	Kg/cm3	1.01/1.06
Loss on Heating (wt) %	ASTM D6	wt %	0.2 max.
Drop in Penetration after heating %	ASTM D5 – D6	%	20 max.

**\*\* Above specifications are subject to change at the time of request.**