



Rhine Middle East LLC
Jafza One, Jebel Ali Free Zone POBOX 34165,
Dubai, United Arab Emirates
Tel: +971 4 81 8618

Bitumen Grade 80 / 100

| Test | Test Method | Unit | Specification |
|--------------------------------------|--------------|--------------------|---------------|
| Penetration @ 25°C | ASTM D5 | mm/10 | 80/100 |
| Softening Points (R&B) | ASTM D36 | °C | 42/50 |
| Ductility @ 25°C | ASTM D113 | Cm | 100 min. |
| Flash Point °C | ASTM D92 | °C | 250 min. |
| Solubility in CS ₂ (wt) % | ASTM D4 | wt% | 99.5 min. |
| Specific Gravity @ 25°C | ASTM D70 | Kg/cm ³ | 1.01/1.06 |
| Loss on Heating (wt) % | ASTM D6 | wt % | 0.2 max. |
| Drop in Penetration after heating % | ASTM D5 – D6 | % | 20 max. |

**** Above specifications are subject to change at the time of request.**