



Rhine Middle East LLC  
Jafza One, Jebel Ali Free Zone POBOX 34165,  
Dubai, United Arab Emirates  
Tel: +971 4 81 8618

## Oxidized Bitumen 105/35

---

Test	Test Method	Unit	Specifications
Specific gravity @25/25 C	ASTM D70	(Kg/m3)	1.05 approx.
Penetration @ 25°C	ASTM D5	mm/10	30/40
Softening point °C	ASTM D36	°C	100/110
Loss on heating(wt) %	ASTM D6	Wt. %	0.2 max
Flashpoint c	ASTM D92	°C	250 min
Solubility in CS <sub>2</sub> (wt) %	ASTM D4	Wt. %	99.5 max
Specific gravity @25/25 C	ASTM D70	(Kg/m3)	1.05 approx.

**\*\* Above specifications are subject to change at the time of request.**