



Rhine Middle East LLC
Jafza One, Jebel Ali Free Zone POBOX 34165,
Dubai, United Arab Emirates
Tel: +971 4 81 8618

Oxidized Bitumen 115/15

| Test | Test Method | Unit | Specifications |
|--------------------------------------|-------------|----------------------|----------------|
| Specific gravity @25/25 C | ASTM D70 | (Kg/m ³) | 1.05 approx. |
| Penetration @ 25°C | ASTM D5 | mm/10 | 10/20 |
| Softening point °C | ASTM D36 | °C | 110/120 |
| Ductility @25 °C | ASTM D113 | Cm | 1.5min |
| Loss on heating(wt) % | ASTM D6 | Wt. % | 0.2 max |
| Flashpoint c | ASTM D92 | °C | 250 min |
| Solubility in CS ₂ (wt) % | ASTM D4 | Wt. % | 99.5 max |

**** Above specifications are subject to change at the time of request.**