



Rhine Middle East LLC
Jafza One, Jebel Ali Free Zone POBOX 34165,
Dubai, United Arab Emirates
Tel: +971 4 81 8618

Oxidized Bitumen 85/25

Test	Test Method	Unit	Specifications
Specific gravity @25/25 C	ASTM D70	(Kg/m ³)	1.05 approx.
Penetration @ 25°C	ASTM D5	mm/10	20/30
Softening point °C	ASTM D36	°C	80/90
Ductility @25 °C	ASTM D113	Cm	3 min
Loss on heating (wt) %	ASTM D6	Wt. %	0.2 max
Flashpoint c	ASTM D92	°C	250 min
Solubility in CS ₂ (wt) %	ASTM D4	Wt. %	99.5 max

**** Above specifications are subject to change at the time of request.**