



Rhine Middle East LLC  
Jafza One, Jebel Ali Free Zone POBOX 34165,  
Dubai, United Arab Emirates  
Tel: +971 4 81 8618

## Oxidized Bitumen 95/25

---

Test	Test Method	Unit	Specifications
Specific gravity @25/25 C	ASTM D70	(Kg/m3)	1.05 approx.
Penetration @ 25°C	ASTM D5	mm/10	20/30
Softening point °c	ASTM D36	°C	90/100
Loss on heating(wt) %	ASTM D6	Wt. %	0.2 max
Flashpoint °c	ASTM D92	°C	250 min
Solubility is CS2(wt) %	ASTM D4	Wt. %	99.5 max
Ductility@25 C	ASTM D113	—	1.5 min

**\*\* Above specifications are subject to change at the time of request.**